




HEA sijas	Augstums h	Platums b	Biezums w	Biezums t	Rādiuss r	Augstums h1	Augstums d	Svars kg/m	m2/m
HEA 100	96	100	5	8	12	80	56	16,7	0,561
HEA 120	114	120	5	8	12	98	74	19,9	0,677
HEA 140	133	140	5.5	8.5	12	116	92	24,7	0,794
HEA 160	152	160	6	9	15	134	104	30,4	0,906
HEA 180	171	180	6	9.5	15	152	122	35,5	1,024
HEA 200	190	200	6.5	10	18	170	134	42,3	1,136
HEA 220	210	220	7	11	18	188	152	50,5	1,255
HEA 240	230	240	7.5	12	21	206	164	60,3	1,369
HEA 260	250	260	7.5	12.5	24	225	177	68,2	1,484
HEA 280	270	280	8	13	24	244	196	76,4	1,603
HEA 300	290	300	8.5	14	27	262	208	88,3	1,717
HEA 320	310	300	9	15.5	27	279	225	97,6	1,756
HEA 340	330	300	9.5	16.5	27	297	243	105	1,795
HEA 360	350	300	10	17.5	27	315	261	112	1,834
HEA 400	390	300	11	19	27	352	298	125	1,912
HEA 450	440	300	11.5	21	27	398	344	140	2,011
HEA 500	490	300	12	23	27	444	390/td>	155	2,11
HEA 550	540	300	12.5	24	27	492	438	166	2,209
HEA 600	590	300	13	25	27	540	486	178	2,308
HEA 650	640	300	13.5	26	27	588	534	190	2,407
HEA 700	690	300	14.5	27	27	636	582	204	2,505
HEA 800	790	300	15	28	30	734	674	224	2,698
HEA 900	890	300	16	30	30	830	770	252	2,896
HEA 1000	990	300	16.5	31	30	928	868	272	3,095




HEB sijas	Augstums h	Platums b	Biezums w	Biezums t	Radiuss r	Augstums h1	Augstums d	Svars kg/m	m2/m
HEB 100	100	100	6	10	12	80	56	20,4	0,567
HEB 120	120	120	6.5	11	12	98	74	26,7	0,686
HEB 140	140	140	7	12	12	116	92	33,7	0,805
HEB 160	160	160	8	13	15	134	104	42,6	0,918
HEB 180	180	180	8.5	14	15	152	122	51,2	1,037
HEB 200	200	200	9	15	18	170	134	61,3	1,151
HEB 220	220	220	9.5	16	18	188	152	71,5	1,27
HEB 240	240	240	10	17	21	206	164	83,2	1,384
HEB 260	260	260	10	17.5	24	225	177	93	1,499
HEB 280	280	280	10.5	18	24	244	196	103	1,618
HEB 300	300	300	11	19	27	262	208	117	1,732
HEB 320	320	300	11.5	20.5	27	279	225	127	1,771
HEB 340	340	300	12	21.5	27	297	243	134	1,81
HEB 360	360	300	12.5	22.5	27	315	261	142	1,849
HEB 400	400	300	13.5	24	27	352	298	155	1,927
HEB 450	450	300	14	26	27	398	344	171	2,026
HEB 500	500	300	14.5	28	27	444	390	187	2,125
HEB 550	550	300	15	29	27	492	438	199	2,224
HEB 600	600	300	15.5	30	27	540	486	212	2,323
HEB 650	650	300	16	31	27	588	534	225	2,422
HEB 700	700	300	17	32	27	636	582	241	2,52
HEB 800	800	300	17.5	33	30	734	674	262	2,713
HEB 900	900	300	18.5	35	30	830	770	291	2,911
HEB 1000	1000	300	19	36	30	928	868	314	3,11




IPE sijas	Augstums h	Platums b	Biezums w	Biezums t	Radiuss R	Augstums h1	Augstums d	Svars kg/m	m2/m
IPE 80	80	46	3.8	5.2	5.0	69.6	59.6	6.0	0,328
IPE 100	100	55	4.1	5.7	7.0	88.6	74.6	8.1	0,4
IPE 120	120	64	4.4	6.3	7.0	107.4	93.4	10.4	0,475
IPE 140	140	73	4.7	6.9	7.0	126.2	112.2	12.9	0,551
IPE 160	160	82	5	7.4	9.0	145.2	127.2	15.8	0,623
IPE 180	180	91	5.3	8	9.0	164.0	146.0	18.8	0,698
IPE 200	200	100	5.6	8.5	12.0	183.0	159.0	22.4	0,768
IPE 220	220	110	5.9	9.2	12.0	201.6	177.6	26.2	0,848
IPE 240	240	120	6.2	9.8	15.0	220.4	190.4	30.7	0,922



IPE 270	270	135	6.6	10.2	15.0	249.6	219.6	36.1	1,041
IPE 300	300	150	7.1	10.7	15.0	278.6	248.6	42.2	1,16
IPE 330	330	160	7.5	11.5	18.0	307.0	271.0	49.1	1,254
IPE 360	360	170	8	12.7	18.0	334.6	298.6	57.1	1,353
IPE 400	400	180	8.6	13.5	21.0	373.0	331.0	66.3	1,467
IPE 450	450	190	9.4	14.6	21.0	420.8	378.8	77.6	1,605
IPE 500	500	200	10.2	16.0	21.0	468.0	426.0	90.7	1,744
IPE 550	550	210	11.1	17.2	24.0	515.6	467.6	106.0	1,877
IPE 600	600	220	12.0	19.0	24.0	562.0	514.0	122.0	2,015



IPN sijas	Augstums h	Platums b	Biezums w	Biezums t	Radiuss R	Augstums d	Svars kg/m	m ² /m
IPN 80	80	42	3.9	5.9	3.9	59.0	5,94	0,304
IPN 100	100	50	4.5	6.8	4.5	75.7	8.34	0,37
IPN 120	120	58	5.1	7.7	5.1	92.4	11.1	0,439
IPN 140	140	66	5.7	8.6	5.1	92.4	14.3	0,502
IPN 160	160	74	6.3	9.5	6.3	125.8	17.9	0,575
IPN 180	180	82	6.9	10.4	6.9	142.4	21.9	0,64
IPN 200	200	90	7.5	11.3	7.5	159.1	26.2	0,709
IPN 220	220	98	8.1	12.2	8.1	175.8	31.1	0,775
IPN 240	240	106	8.7	13.1	8.7	192.5	36.2	0,844
IPN 260	260	113	9.4	14.1	9.4	208.9	41.9	0,906
IPN 280	280	119	10.1	15.2	10.1	225.1	47.9	0,966
IPN 300	300	125	10.8	16.2	10.8	241.6	54.2	1,03
IPN 320	320	131	11.5	17.3	11.6	257.9	61.0	1,09
IPN 340	340	137	12.2	18.3	12.2	274.3	68.0	1,15
IPN 360	360	143	13	19.5	13.0	290.0	76.1	1,21
IPN 380	380	149	13.7	20.5	13.7	306.7	84.0	1,27
IPN 400	400	155	14.4	21.6	14.4	306.7	92.4	1,33
IPN 450	450	170	16.2	24.3	16.2	363.6	115	1,48
IPN 500	500	185	18	27	18.0	404.3	141	1,63
IPN 550	550	200	19	30	19.0	445.6	166	1,8
IPN 600	600	215	21.6	32.4	21.6	485.8	199	1,92



HEM sijas	Augstums h	Platums b	Biezums w	Biezums t	Radiuss r	Augstums h1	Augstums d	Svars kg/m	m2/m
HEM 100	120	106	12	20	12	80	56	41.8	0,619
HEM 120	140	126	12.5	21	12	98	74	52.1	0,738
HEM 140	160	146	13	22	12	116	92	63.2	0,857
HEM 160	180	166	14	23	15	134	104	76.2	0,97
HEM 180	200	186	14.5	24	15	152	122	88.9	1,089
HEM 200	220	206	15	25	18	170	134	103	1,203
HEM 220	240	226	15.5	26	18	188	152	117	1,322
HEM 240	270	248	18	32	21	206	164	157	1,46
HEM 260	290	268	18	32.5	24	225	177	172	1,575
HEM 280	310	288	18.5	33	24	244	196	189	1,694
HEM 300	340	310	21	39	27	262	208	238	1,832
HEM 320	359	309	21	40	27	279	225	246	1,866
HEM 340	377	309	21	40	27	297	243	248	1,902
HEM 360	395	308	21	40	27	315	261	250	1,934
HEM 400	432	307	21	40	27	352	298	256	2,004
HEM 450	478	307	21	40	27	398	344	263	2,096
HEM 500	524	306	21	40	27	444	390	270	2,184
HEM 550	572	306	21	40	27	492	438	278	2,28
HEM 600	620	305	21	40	27	540	486	285	2,372
HEM 650	668	305	21	40	27	588	534	293	2,468
HEM 700	716	304	21	40	27	636	582	301	2,56
HEM 800	814	303	21	40	30	734	674	317	2,746
HEM 900	910	302	21	40	30	830	770	333	2,934
HEM 1000	1008	302	21	40	30	928	868	349	3,13

